

(19) World Intellectual Property Organization
International Bureau



(43) International Publication Date
12 June 2003 (12.06.2003)


PCT

(10) International Publication Number
WO 03/048047 A1

- (51) International Patent Classification⁷: C01G 9/02, B82B 3/00
- (21) International Application Number: PCT/KR02/02312
- (22) International Filing Date: 7 December 2002 (07.12.2002)
- (25) Filing Language: Korean
- (26) Publication Language: English
- (30) Priority Data:
10-2001-0077290
7 December 2001 (07.12.2001) KR
- (71) Applicants and
(72) Inventors: PARK, Sung [KR/KR]; 101-801, Hyundai 1st APT, 653 Gaepo-dong, Gangnam-gu, 135-973 Seoul (KR).
LEE, Ju-Hyeon [KR/KR]; 1466, Ssangyong-dong, Cheonan, 330-090 Choongnam (KR).
- (73) Inventor; and
(75) Inventor/Applicant (for US only): LEE, Kang-Ryul [KR/KR]; 38-2 San, Nam-dong, Yongin-si, 449-030 Gyeonggi-do (KR).
- (74) Agents: LEE, Sei-Jin et al.; 17th Floor, City Air Tower, 159-9 Samsung-dong, Gangnam-gu, 135-973 Seoul (KR).
- (81) Designated States (national): AE, AG, AL, AM, AT, AU, AZ, BA, BB, BG, BR, BY, BZ, CA, CH, CN, CO, CR, CU, CZ, DE, DK, DM, DZ, EC, EE, ES, FI, GB, GD, GE, GH, GM, HR, HU, ID, IL, IN, IS, JP, KE, KG, KP, KZ, LC, LK, LR, LS, LT, LU, LV, MA, MD, MG, MK, MN, MW, MX, MZ, NO, NZ, OM, PH, PL, PT, RO, RU, SD, SE, SG, SK, SL, TJ, TM, TN, TR, TT, TZ, UA, UG, US, UZ, VC, VN, YU, ZA, ZM, ZW.
- (84) Designated States (regional): ARIPO patent (GH, GM, KE, LS, MW, MZ, SD, SL, SZ, TZ, UG, ZM, ZW), Eurasian patent (AM, AZ, BY, KG, KZ, MD, RU, TJ, TM), European patent (AT, BE, BG, CH, CY, CZ, DE, DK, EE,

[Continued on next page]

(54) Title: A METHOD FOR PREPARING ZnO NANOPOWDER



(57) Abstract: Disclosed is a method of preparing ZnO nanopowder according to a non-equilibrium synthetic process, comprising adding an organic substance containing an amine group or a carboxyl group as a fuel material to an aqueous solution having Zn^{2+} and (NO_3) ions to prepare a mixed solution, and heating the resulting solution with agitation. The method is advantageous in that the ZnO nanopowder has excellent valuable metal recovery and harmful organic substance decomposition efficiency, and the highly pure ZnO nanopowder with nano-sized particles is prepared in commercial quantities.